



PRODUCTS, INC.

918 N. Union Street
Appleton, WI 54911
920-739-8685
or 1-800-221-6381
Fax: 920-739-8704
EMAIL: CDPEPOXY@AOL.COM

Epoxy & fiberglass flooring, seamless fiberglass wall systems, sealers, high performance coating systems, and industrial cleaners

PRODUCT BULLETIN

#1120 EPOXY BLOCK FILLER

DESCRIPTION

#1120 EPOXY FLOCK FILLER IS A TWO COMPONENT, HIGH RESIN SOLIDS, THICKENED EPOXY RESIN/POLYAMIDE COATING. #1120 EPOXY BLOCK FILLER IS PROVIDED IN WHITE AND MAY BE TINTED AT THE CUSTOMER'S REQUEST. THIS COATING IS DESIGNED GENERAL PURPOSE, BLOCK AND CONCRETE PANEL BLOCK FILLER AND IS TYPICALLY USED UNDER OTHER EPOXY OR URETHANE COATINGS. AVAILABLE IN WHITE.

USES

#1120 EPOXY BLOCK FILLER IS TYPICALLY USED WHERE A MAJOR STEP UP IN WALL SURFACE DURABILITY DURABILITY FROM A LATEX BLOCK FILLER IS REQUIRED. #1120 IS ESPECIALLY USEFUL FOR CHEMICAL EXPOSURE, WEAR SITUATIONS OR FREQUENT WASH UPS.

APPLICATION

STIR BOTH PARTS THOROUGHLY, MIX PART A EPOXY AND PART B HARDENER 1 :1 BY VOLUME AND LET INDUCT 30 MINUTES PRIOR TO USE. APPLY BY BRUSH, ROLLER OR SPRAY AT A RATE OF 100-200 SQFT. PER GAL. TWO TOP COATS MAY BE NEEDED TO FILL POROUS SURFACES. TACK FREE TIME IS 6-8 HOURS @ 70F, WITH LIMITED USE ALLOWED IN 24 HOURS, AND FULL USE AFTER 48 HOURS. RECOAT WITHIN 24 HOURS OF INITIAL TACK FREE TIME WHEN USING HIGHER PERFORMANCE TOP COAT SYSTEMS. DO NOT APPLY IF THE TEMPERATURE IS BELOW 60F OR ABOVE 110F. THINNING FOR SPRAYING SHOULD BE WITH #501 SOLVENT OR XYLOL.

NOTE:

TO THE BEST OF OUR KNOWLEDGE, THE INFORMATION HEREIN IS ACCURATE. HOWEVER C.D. PRODUCTS, INC. ASSUMES NO LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN. THE FINAL DETERMINATION OF SUITABILITY OF ANY MATERIAL IS THE SOLE RESPONSIBILITY OF THE USER. ALL MATERIALS MAY PRESENT UNKNOWN HEALTH HAZARDS AND SHOULD BE USED WITH CAUTION. ALTHOUGH CERTAIN HAZARDS ARE DESCRIBED HEREIN, WE CANNOT GUARANTEE THAT THESE ARE THE ONLY HAZARDS WHICH EXIST. (6/15/90)