



PRODUCTS, INC.

918 N. UNION STREET
APPLETON, WI 54911
920-739-8685
OR 1-800-221-6381
FAX: 920-739-8704

WWW.CONCRETEDEFENSE.COM

EMAIL: CDPEPOXY@AOL.COM

EPOXY & FIBERGLASS FLOORING, SEAMLESS FIBERGLASS WALL SYSTEMS, SEALERS,
HIGH PERFORMANCE coating systems, and industrial cleaners

PRODUCT BULLETIN

#2200 ALIPHATIC MCU SEALER

DESCRIPTION: #2200 ALIPHATIC MOISTURE CURE URETHANE SEALER is a clear high performance, UV stable coating. The #2200 is a tough, chemical resistant, one component aliphatic urethane. It provides an easy to apply urethane gloss coating which is especially useful as an industrial concrete floor coating and as a gloss top coat for epoxy coatings. AVAILABLE IN STANDARD COLORS.

USES: #2200 may be used as a general purpose industrial urethane coating although most uses are as a concrete floor coating/sealer and as a top coat for other coatings. As a concrete coating it provides a good wearing, attractive system for heavy use and general chemical exposure areas. #2200 may be used in sun lit areas where clarity and light stability are important.

APPLICATION: For best results #2200 should be applied over a cleaned concrete surface primed with a suitable EPOXY PRIMER such as #1020 PENETRATING EPOXY, or NUPRIME. For a showplace shine, a minimum of two coats of #2200 are suggested, each applied at 300-350 sqft./gal. As a gloss top coat for other coatings one coat is required. Partial containers should be tightly sealed when not in use. For multiple top coats each coat should follow within 12 hours of the last. Future recoating may be done after the surface has been thoroughly cleaned, abraded and tack wiped with SURFPREP #102 prior to recoating.

SPECIFICATIONS:

Solids	45%	Gardner Color 1	2
Tack Free	3Hr	UV Stability	Excellent
Limited Use	12Hr	Pencil Hardness	3H
Full Use	24Hr	Gloss	Excellent
Tabor Abrasion	18 mg lost	Solvent Resistance	Excellent

NOTE: TO THE BEST OF OUR KNOWLEDGE, THE INFORMATION CONTAINED HEREIN IS ACCURATE. HOWEVER C.D. PRODUCTS, INC. ASSUMES NO LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN. THE FINAL DETERMINATION OF SUITABILITY OF ANY MATERIAL IS THE SOLE RESPONSIBILITY OF THE USER. ALL MATERIALS MAY PRESENT UNKNOWN HEALTH HAZARDS AND SHOULD BE USED WITH CAUTION. ALTHOUGH CERTAIN HAZARDS ARE DESCRIBED HEREIN, WE CANNOT GUARANTEE THAT THESE ARE THE ONLY HAZARDS WHICH EXIST.