



# PRODUCTS, INC.

918 N. UNION STREET  
APPLETON, WI 54911  
(920) 739-8685  
1-800-221-638  
FAX (920) 739-8704

---

**EPOXY & FIBERGLASS FLOORING, SEAMLESS FIBERGLASS WALL SYSTEMS, SEALERS,  
HIGH PERFORMANCE COATING SYSTEMS, AND INDUSTRIAL CLEANERS**

---

## PRODUCT BULLETIN #1301 PENETRATING SEALER

**DESCRIPTION:** #1301 PENETRATING PRIMER is a lower solids version of the #1300 for use as a penetrating sealer or primer. It is supplied as a 33% solids solution possessing several key features. Excellent hardness, short cure time, cures to 20f. Excellent general chemical and outstanding solvent resistance.

**USE:** the #1300 or #1301 system may be used anywhere a tough, hard, high gloss surface is desired. Its chemical resistance makes it a good choice where a broad range of chemical splashes and exposure conditions will be encountered. Its outstanding solvent resistance makes it a good choice in printing plants, garages and aircraft hangars.

**APPLICATION:** Mix 1 part PART A with 1 part PART B by volume, let induct 30 minutes and apply with roller or sprayer. Pot life is six hours or less depending on temperature. Dust free time is 4 hours, limited use may be permitted in 24 hours. As a surface sealer system two coats are recommended both applied at 300-350 sqft./gal. A third coat may be applied to over fill the concrete and provide a minimum top surface.

### **SPECIFICATIONS:**

Volume Solids	33%	Clear	Potlife	4-/Hr
Dry Film Color	Gardner	2	Adhesion	Excellent
Film Hardness		3H	Gloss	90

**CHEMICAL RESISTANCE:** Exceeds 1000 Double Rubs Mek, Mibk, Methelene Chloride, Methanol, Normal Propyl Acetate, Perchloroethelene, Skydrol.

7 Days Immersion/No Effect: Xylol, Mek, Methanol, Normal Propyl Acetate, Di Water, 10% Sulfuric Acid, 10% HCl, 10% Ammonium Hydroxide Skydrol.

7 Day Immersion/Some Effect: Glychol Ether EB-Softens, 10% Nitric Acid-Stains

NOTE: TO THE BEST OF OUR KNOWLEDGE, THE INFORMATION CONTAINED HEREIN IS ACCURATE. HOWEVER C.D. PRODUCTS INC. ASSUMES NO LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN. THE FINAL DETERMINATION OF SUITABILITY OF ANY MATERIAL IS THE SOLE RESPONSE OF THE USER. ALL MATERIALS MAY PRESENT UNKNOWN HEALTH HAZARDS AND SHOULD BE USED WITH CAUTION. ALTHOUGH CERTAIN HAZARDS ARE DESCRIBED HEREIN, WE CANNOT GUARANTY THAT THESE ARE THE ONLY HAZARDS WHICH EXIST.